This listing of claims will replace all prior versions and listings of claims in the application.

Listing of Claims:

Claims 1-29(canceled).

30 (Currently Amended) A data storage media including a substrate and a recording layer, said recording layer containing uniformly distributed in said layer a mixture of at least a first and second cyanine dye-TCNQ complex; said first cyanine dye-TCNQ complex having a formula (II):



(II)

wherein Q and Q' each form a ~~fix membered~~ six-membered carbon containing aromatic ring;

R_1 is $-CH_2C_6H_4COOCH_3$;

R_2 is a linear butyl group;

TCNQ is 7,7',8,8'-tetracyanoquinodimethane;

m and n are each 1; said second cyanine dye-TCNQ complex having a formula

(IV)



(IV)

wherein Q and Q' each form a six membered carbon containing aromatic ring;

R_1 is $-CH_2C_6H_4COOCH_3$;

R_2 is $CH_2C_6H_4COOCH_3$;

n is an integer of 2;

m is 1; and the weight percentage of complex (IV) to complex (II) is from 0.5 to about 20%.

31 (Previously presented) The data storage media of claim 30 also containing a reflection layer which is selected from the group consisting of Au, Ag, Al, Cu, Cr and alloys thereof.

32 (Previously presented) The data storage media of claim 30 wherein the recording layer has a thickness of about 500 Å to about 2000 Å.

33 (Currently Amended) The reflection layer of claim ~~30~~ 31 having a thickness of about 500 Å to about 1000 Å.

34 (Previously presented) The data storage media of claim 30 which is a high density recordable optical disc.

35 (Previously presented) The data storage media of claim 30 wherein the weight percentage of complex (IV) to complex (II) is from 2 to 10%.

36 (Previously presented) The data storage media of claim 35 also containing a reflection layer which is selected from the group consisting of Au, Ag, Al, Cu, Cr and alloys thereof.

37 (Previously presented) The data storage media of claim 35 wherein the recording layer has a thickness of about 500 Å to about 2000 Å.

38 (Currently Amended) The reflection layer of claim ~~35~~ 36 having a thickness of about 500 Å to about 1000 Å.

39 (Previously presented) The data storage media of claim 35 which is a high density recordable optical disc.

40 (Currently Amended) A data storage media including a substrate and a recording layer, said recording layer containing uniformly distributed in said layer a mixture of at least a first and second cyanine dye-TCNQ complex; said first cyanine dye-TCNQ complex having a formula (II):



(II)

wherein Q and Q' each form a ~~fix membered~~ six-membered carbon containing aromatic ring;

R_1 is $-CH_2C_6H_4COOCH_3$;

R_2 is an alkyl group;

TCNQ is 7,7',8,8'-tetracyanoquinodimethane;

m and n are each 1; said second cyanine dye-TCNQ complex having a formula

(IV)



(IV)

wherein Q and Q' each form a six membered carbon containing aromatic ring;

R_1 is $-CH_2C_6H_4COOCH_3$;

R_2 is $CH_2C_6H_4COOCH_3$;

n is an integer of 2;

m is 1; and the weight percentage of complex (IV) to complex (II) is from 0.5 to about 20%.

41 (Previously presented) The data storage media of claim 40 also containing a reflection layer which is selected from the group consisting of Au, Ag, Al, Cu, Cr and alloys thereof.

42 (Previously presented) The data storage media of claim 40 wherein the recording layer has a thickness of about 500 Å to about 2000 Å.

43 (Currently Amended) The reflection layer of claim ~~40~~ 41 having a thickness of about 500 Å to about 1000 Å.

44 (Previously presented) The data storage media of claim 40 which is a high density recordable optical disc.

45 (Previously presented) The data storage media of claim 40 wherein the weight percentage of complex (IV) to complex (II) is from 2 to 10%.

46 (Previously presented) The data storage media of claim 45 also containing a reflection layer which is selected from the group consisting of Au, Ag, Al, Cu, Cr and alloys thereof.

47 (Previously presented) The data storage media of claim 45 wherein the recording layer has a thickness of about 500 Å to about 2000 Å.

48 (Currently Amended) The reflection layer of claim ~~45~~ 46 having a thickness of about 500 Å to about 1000 Å.

49 (Previously presented) The data storage media of claim 45 which is a high density recordable optical disc.